



## OXIDIZED BITUMEN 90/15

SPECIFICATION OF OXIDIZED BITUMEN 90/15		TEST METHOD
Specific gravity @25/25 C	1.05 approx	D-70
Penetration @25C	20/25	D-5
Softening point C	85/95	D-36
Ductility@25C	1.5min	D-113
Loss on heating (wt)%	0.2max	D-6
Flash point C	260min	D-92
Solubility in CS2 (wt)%	99min	D-4