



## BITUMEN 80/100

<b>Property / Unit</b>	<b>Specification</b>	<b>Method</b>
Specific Gravity, 25°C, (kg/m <sup>3</sup> )	1.05 Approx	ASTM D70
Penetration, 25°C, (mm/10)	80-100	ASTM D5
Softening Point (°C)	45-52	ASTM D36
Ductility, 25°t, (cm/s)	100 Min	ASTM D113
Loss On Heating (WT%)	0.2 Max	ASTM D6
Flash Point (°C)	225 Min	ASTM D92
Solubility in sc2 (WT%)	>99	ASTM D4