



Product Name: Bitumen 200/300
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	200/300	ASTM D5	200–300	245
Softening Point	30/37	ASTM D36	30–37	34
Ductility @ 25°C	100 Min	ASTM D113	≥100	120
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.11
Flash Point	220 Min	ASTM D92	≥220	268
Solubility in CS2	99.0 Min	ASTM D4	≥99.0	99.2
Appearance	Black, solid	Visual	Black, solid	Black, solid