



Product Name: Bitumen 20/30
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	20/30	ASTM D5	20-30	24
Softening Point	55/63	ASTM D36	55-63	59
Ductility @ 25°C	100 Min	ASTM D113	≥100	105
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.06
Flash Point	250 Min	ASTM D92	≥250	322
Solubility in CS2	99.5 Min	ASTM D4	≥99.5	99.9
Appearance	Black, solid	Visual	Black, solid	Black, solid