



Product Name: Bitumen 30/40
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	30/40	ASTM D5	30-40	36
Softening Point	48/56	ASTM D36	48-56	54
Ductility @ 25°C	100 Min	ASTM D113	≥100	115
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.07
Flash Point	250 Min	ASTM D92	≥250	318
Solubility in CS ₂	99.5 Min	ASTM D4	≥99.5	99.9
Appearance	Black, solid	Visual	Black, solid	Black, solid