



Product Name: Bitumen 50/70
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	50/70	ASTM D5	50-70	61
Softening Point	47/56	ASTM D36	47-56	53
Ductility @ 25°C	100 Min	ASTM D113	≥100	130
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.09
Flash Point	250 Min	ASTM D92	≥250	325
Solubility in CS ₂	99.5 Min	ASTM D4	≥99.5	99.7
Appearance	Black, solid	Visual	Black, solid	Black, solid