

**Product Name: Bitumen 60/70****HS Code: 27132000**

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	60/70	ASTM D5	60–70	67
Softening Point	49/56	ASTM D36	49–56	52
Ductility @ 25°C	100 Min	ASTM D113	≥100	120
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.1
Flash Point	250 Min	ASTM D92	≥250	320
Solubility in CS ₂	99.5 Min	ASTM D4	≥99.5	99.8
Appearance	Black, solid	Visual	Black, solid	Black, solid