



Product Name: Bitumen 80/100
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Penetration @ 25°C	80/100	ASTM D5	80–100	92
Softening Point	42/50	ASTM D36	42–50	46
Ductility @ 25°C	100 Min	ASTM D113	≥100	125
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.12
Flash Point	250 Min	ASTM D92	≥250	310
Solubility in CS ₂	99.5 Min	ASTM D4	≥99.5	99.7
Appearance	Black, solid	Visual	Black, solid	Black, solid