



Product Name: Cutback PMB 40
HS Code: 27150000

Property	Typical Value	Test Method	Specification / Limit	Result
Kinematic Viscosity @ 60°C (cSt)	350	ASTM D2170	300 – 400	355
Flash Point (°C, Tag Closed Cup)	65 Min	ASTM D56	≥ 65	68
Penetration @ 25°C (0.1 mm)	40	ASTM D5	35 – 45	41
Softening Point (°C)	55	ASTM D36	50 – 60	56
Distillation Test – 225°C Distillate (% by volume)	25	ASTM D402	≤ 30	24
Distillation Test – 360°C Distillate (% by volume)	55	ASTM D402	≤ 60	54
Solubility in CS ₂ (%)	99.0 Min	ASTM D4	≥ 99.0	99.4
Specific Gravity @ 25°C	1.02	ASTM D70	1.00 – 1.05	1.02
Water Content (%)	0.2 Max	ASTM D95	≤ 0.2	0.05
Appearance	Black, viscous liquid	Visual	Black, viscous liquid	Black, viscous liquid

