



Product Name: Oxidized Bitumen 115/15
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Softening Point	115	ASTM D36	110–120	116
Penetration @ 25°C	15	ASTM D5	10–20	14
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.07
Flash Point	250 Min	ASTM D92	≥250	305
Solubility in CS ₂	99.0 Min	ASTM D4	≥99.0	99.4
Specific Gravity @25°C	1.05	ASTM D70	1.0–1.1	1.06
Appearance	Black, solid	Visual	Black, solid	Black, solid