



Product Name: Oxidized Bitumen 75/25
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Softening Point	75	ASTM D36	70-80	77
Penetration @ 25°C	25	ASTM D5	20-30	26
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.08
Flash Point	250 Min	ASTM D92	≥250	295
Solubility in CS ₂	99.0 Min	ASTM D4	≥99.0	99.3
Specific Gravity @25°C	1.05	ASTM D70	1.0-1.1	1.04
Appearance	Black, solid	Visual	Black, solid	Black, solid