



Product Name: Oxidized Bitumen 85/25
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Softening Point	85	ASTM D36	80-90	86
Penetration @ 25°C	25	ASTM D5	20-30	24
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.07
Flash Point	250 Min	ASTM D92	≥250	297
Solubility in CS ₂	99.0 Min	ASTM D4	≥99.0	99.5
Specific Gravity @25°C	1.05	ASTM D70	1.0-1.1	1.06
Appearance	Black, solid	Visual	Black, solid	Black, solid