



Product Name: Oxidized Bitumen 85/35
HS Code: 27132000

Property	Typical Value	Test Method	Specification / Limit	Result
Softening Point	85	ASTM D36	80–90	87
Penetration @ 25°C	35	ASTM D5	30–40	34
Loss on Heating	0.2 Max	ASTM D6	≤0.2	0.08
Flash Point	250 Min	ASTM D92	≥250	295
Solubility in CS ₂	99.0 Min	ASTM D4	≥99.0	99.5
Specific Gravity @25°C	1.05	ASTM D70	1.0–1.1	1.05
Appearance	Black, solid	Visual	Black, solid	Black, solid